



KAPCI
COATINGS

For professional use only

Issue: June 2018
Superseded: March 2016

Kapci 3150 Matt 2K MS Clearcoat

Product description

Kapci 3150 Matt is a 2K medium solids acrylic clearcoat designed for repairs of surfaces requiring matt finish. It delivers flexible and matt finish, and is used in conjunction with standard Kapci hardeners - 653 Extra Fast, 652 Fast, 651 Normal, or 656 Slow.

Substrates

Kapci 3150 Matt clearcoat should be applied over Kapcibase and Laticobase solvent-based basecoat colors or properly prepared old paint work in sound conditions. Existing job should be properly sanded and degreased prior to applying Kapci 3100 Matt clearcoat.


Application




Mixing ratio:
100:50:30
(2:1:0.6)

100% Kapci 3150 Matt Clearcoat
50% Kapci MS Hardeners: 653 Extra Fast, 652 Fast, 651 Normal or 656 Slow
30% Kapci 2K Thinners: 600F Fast, 600 Normal, 601 Slow or 602 Extra Slow

Note: Select appropriate thinner and hardener according to ambient temperature, air movement, and size of the surface to be clearcoated.



Use mixing ruler



Application viscosity:
15-18 s (DIN4/20°C)

These products are for the professional painting of automotive vehicles only after reference to the manufacturer's Material Safety Data Sheets (MSDS)

Rev (02) 06/2018




KAPCI
COATINGS

For professional use only

Issue: June 2018

Superseded: March 2016



Pot life:
4 h at 20°C



Spray gun tips:


Compliant: 1.2-1.3 mm; Air pressure: 2 bar (26-29 psi) at the air inlet
HVLP: 1.2-1.3 mm; Air pressure: 0.6-0.7 bar (8-10 psi) at the tip
Conventional: 1.2-1.3 mm; Air pressure: 3.0-3.5 bar (45-50 psi) inlet

For best overall results, refer to the spray gun manufacturer's recommendation.



Number of coats:

Apply 2 normal coats.
Total dry film thickness 50-55 microns.



Flash off time:

5-10 min/20°C between coats (until matt)
20 min/20°C before baking



Drying time:

15 h/20°C
30 min/60°C



IR drying:

Short wave*: 10-15 min

*Guideline for IR equipment. Refer to the IR equipment manufacturer's instruction for sets-up.

General notes

Choice of hardener

Kapci offers a range of hardeners to meet every type and size of car refinish under all conditions.

The recommendations below are for guidance only:

Kapci 653 Extra Fast hardener is recommended for temperatures below 20°C and small size of repair.

Kapci 652 Fast hardener is used for medium sized repair and temperature up to 25°C.

Kapci 651 Normal hardener is suitable for large areas, i.e. for all repairs at temperature up to 30°C.

Kapci 656 Slow hardener should be used when temperature exceeds 30°C.



KAPCI
COATINGS

For professional use only

Issue: June 2018

Superseded: March 2016

Other tips

1. Kapci 3150 Matt Clearcoat has gloss 10-15 GU at $\angle 85$. It cannot be polished as the polishing process will gloss the clearcoat.
2. For optimum application, ensure that both spray booth temperature and paint temperature is between 20°C and 25°C.

VOC (2004/42/EC)

2004/42/IIB(e)(840)560

The EU limit value for this product (product category: IIB.e) in ready for use form is maximum 840 g/l of VOC.

The VOC content of this product in ready for use form is maximum 560 g/l.

Health and Safety

1. For full Health and Safety information refer to Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: These products are for professional use only. The information in this Technical Data Sheet is based on our best knowledge and given for information purposes only without any obligation as we do not have control over the quality and conditions of the surface, or over many factors affecting the use and application of the product. Always read the Material Safety Data Sheet and the Technical Data Sheet for this product if available.

Rev (02) 06/2018